

8/13/2018

Product: **2500**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Natural	
Density (lbs. / ft ³)	1.05 - 1.25	ASTM D-3574-17
Indent Force Deflection @ 25%	30 - 36	ASTM D-3574-17
Compression Set at 50% comp.(%)	10	ASTM D-3574-17
Tensile Strength (psi)	10	ASTM D-3574-17
Tear Strength (lbs./lin inch)	1	ASTM D-3574-17
Elongation (%)	100	ASTM D-3574-17

This product has been tested and found to comply with Section 3 of the California Technical Bulletin 117-2013.

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

WARNING: URETHANE FOAM IS FLAMMABLE!
Urethane Foam should not be exposed to open flame or other ignition sources.
Urethanes burn rapidly with great heat and release gases which are extremely hazardous.