

11/8/2018

Product: **7400**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Charcoal Grey	
Density (lbs / ft <sup>3</sup> )	3.6 - 4.4	ASTM D-3574-01
Compression Deflection @ 25% (psi)	0.50 min	ASTM D-3574-01
Tensile Strength (psi)	18 min	ASTM D-3574-01
Elongation (%)	200 min	ASTM D-3574-01
Tear Strength (lbs / lin inch)	2.0 min	ASTM D-3574-01
Flame Resistance	pass pass	FMVSS302 UL94 HF-1

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

**WARNING: URETHANE FOAM IS FLAMMABLE!**

Urethane Foam should not be exposed to open flame or other ignition sources.  
Urethanes burn rapidly with great heat and release gases which are extremely hazardous.

4560 112th Street Northwest Maple Lake, MN 55358

Ph. 320-963-5042