

9/19/2018

 Product: **ABL160**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Blue	
Density (lbs / ft3)	1.6 - 1.8	ASTM D 3575-93
Compressive Strength – @25% Vertical Direction (psi) @50%	5.8 13	ASTM D 3575-93 Suffix D
Compression Set (%)	16	ASTM D 3575-93 Suffix B
Compression Creep (%)	<12% @ 2.0 psi	ASTM D 3575-93 Suffix BB
Tensile Strength (psi)	24	ASTM D 3575-93 Suffix T
Tear Resistance (lbs/inch)	7.5	ASTM D 3575-93 Suffix G
Cell Size (mm)	1.9	ASTM D-3576 Modified
Water Absorption (lbs / ft2)	<0.3	ASTM D 3575-93 Suffix L
Thermal Stability	<5%	ASTM D 3575-93 Suffix S
Thermal Conductivity k-Value	0.49	ASTM C518-91
Thermal Resistance R-Value	2.0	ASTM C518-91

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.