

6/20/2018

 Product: **EPE13WH**

| <u>Physical Property</u> | <u>Value</u> | <u>Test Method</u> |
|--|----------------|--------------------------|
| Color | White | |
| Density (lbs / ft3) | 1.3 | ASTM D 3575 |
| Compressive Strength – @25% Vertical Direction (psi) @50% | 8.8 16.6 | ASTM D 3575-93 Suffix D |
| Compression Set @ 25% / 50% (%) | 3.0 / 14 | ASTM D 3575-93 Suffix B |
| Compression Creep (%) | 2.8% @ 1.0 psi | ASTM D 3575-93 Suffix BB |
| Tensile Strength (psi) | 40 | ASTM D 3575-93 Suffix T |
| Tear Resistance (lbs/inch) | 14 | ASTM D 3575-93 Suffix G |
| Buoyancy (pcf) | 60.6 | ASTM D 3575 |
| Water Absorption (%) | <5% in volume | ASTM D 3575 |
| Tensile Elongation (%) | 38 | ASTM D 3575-93 Suffix S |
| Thermal Conductivity k-Value | 0.26 | ASTM C177 |
| Thermal Resistance R-Value | 4 | ASTM C177 |
| Flammability | pass | FMVSS302 |

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

4560 112th Street Northwest Maple Lake, MN 55358

Ph. 320-963-5042