

11/8/2018

Product: **EPS20**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	White	
Density (lbs / ft ³)	1.80 - 2.00	ASTM D1622
Compressive 10% deformation (psi)	20 - 25	ASTM D1621
Tensile Strength (psi)	23-27	ASTM D1623
Shear (psi)	33-37	ASTM D732
Water absorption (%)	<2	ASTM C272
Maximum service temp (f)	167-180	Recommended
Thermal Conductivity (BTU/hr)	0.210	ASTM C177
Thermal Resistance (R-Value at 75F)	4.35	

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.