

11/8/2018

Product: **XL2000/EVA**

| <u>Physical Property</u>                      | <u>Value</u>     | <u>Test Method</u>      |
|---|------------------|-------------------------|
| Color   | Natural          |                         |
| Density (lbs / ft3)                           | 2.0              | ASTM D 3575-93          |
| Compressive Strength – @25%                   | 6.8              | ASTM D 3575-93 Suffix D |
| Compression Set (%)                           | 15.4             | ASTM D 3575-93 Suffix B |
| Tensile Strength (psi)                        | 53.9             | ASTM D 3575-93 Suffix T |
| Tear Resistance (lbs/inch)                    | 12.9             | ASTM D 3575-93 Suffix G |
| Water Absorption (lbs / ft2)                  | <1               | ASTM D 3575-93 Suffix L |
| Working Temperature Range                     | -76 to 194 deg F |                         |
| Thermal Conductivity<br>(btu/hr/inch ft/degF) | 0.26             | ASTM C177               |
| Elongation (% to break)                       | 345              | ASTM D 3575-93          |

Note: blended with EVA

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.