

11/8/2018

 Product: **XL2000**

| <u>Physical Property</u> | <u>Value</u> | <u>Test Method</u> |
|---|------------------|-------------------------|
| Color | Natural | |
| Density (lbs / ft3) | 2.0 | ASTM D 3575-93 |
| Compressive Strength – @25% | 8.2 | ASTM D 3575-93 Suffix D |
| Compression Set (%) | 18 | ASTM D 3575-93 Suffix B |
| Tensile Strength (psi) | 55.4 | ASTM D 3575-93 Suffix T |
| Tear Resistance (lbs/inch) | 12.5 | ASTM D 3575-93 Suffix G |
| Water Absorption (lbs / ft2) | <1 | ASTM D 3575-93 Suffix L |
| Working Temperature Range | -76 to 194 deg F | |
| Thermal Conductivity (btu/hr/inch ft/degF) | 0.26 | ASTM C177 |
| Elongation (% to break) | 290 | ASTM D 3575-93 |

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Foam Fabricators of Minnesota does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.